(19)【発行国】日本国特許庁（ＪＰ）

(12)【公報種別】公開特許公報（Ａ）

(11)【公開番号】特開２０００－４５１２８（Ｐ２０００－４５１２８Ａ）|

(43)【公開日】平成１２年２月１５日（２０００．２．１５）

(54)【発明の名称】高耐熱性無機繊維

(51)【国際特許分類第７版】　Ｄ０１Ｆ　９/０８
　　Ｃ０４Ｂ　３５/５０

【ＦＩ】　Ｄ０１Ｆ　９/０８　　Ｚ　　Ｃ０４Ｂ　３５/５０

【審査請求】未請求|

【請求項の数】５

【出願形態】ＯＬ

【全頁数】６

(21)【出願番号】特願平１０－２０８２２９

(22)【出願日】平成１０年７月２３日（１９９８．７．２３）

(71)【出願人】

【識別番号】０００００２０６

【氏名又は名称】宇部興産株式会社

【住所又は居所】山口県宇部市西本町１丁目１２番３２号

(71)【出願人】

【識別番号】５９１１１２６２５

【氏名又は名称】井上　明久

【住所又は居所】宮城県仙台市青葉区川内元支倉３５番地　川内住宅１１－８０６

(72)【発明者】

【氏名】井上　明久|

(19) [Publication Office] Japanese Patent Office (JP)

(12) [Kind of Document] Japan Unexamined Patent Publication (A)

(11) [Publication Number of Unexamined Application] Japan Unexamined Patent Publication 2000 - 45128(P2000 - 45128A)

(43) [Publication Date of Unexamined Application] 2000 February 15 day (2000.2.15)

(54) [Title of Invention] HIGH HEAT RESISTANCE INORGANIC FIBER

(51) [International Patent Classification 7th Edition]　D01F 9/08　　C04B 35/50

[FI]　D01F 9/08　　Z　　C04B 35/50

[Request for Examination] Examination not requested

[Number of Claims] 5

[Form of Application] OL

[Number of Pages in Document] 6

(21) [Application Number] Japan Patent Application Hei 10 - 208229

(22) [Application Date] 1998 July 23 days (1998.7.23)

(71) [Applicant]

[Applicant Code] 000000206

[Name] UBE INDUSTRIES LTD. (DB 69-056-0008)

[Address] Yamaguchi Prefecture Ube City Nishihommachi 1-1232

(71) [Applicant]

[Applicant Code] 591112625

[Name] INOUE　AKIHISA

[Address] Miyagi Prefecture Sendai City Aoba-ku Kawauchi Mohasekura 35　Kawauchi Residence 11 - 806

(72) [Inventor]

[Name] Inoue　Akihisa

【住所又は居所】宮城県仙台市青葉区川内元支倉３５番地　川内住宅１１－８０６

(72)【発明者】

【氏名】和久　芳春

【住所又は居所】山口県宇部市大字小串１９７８番地の５　宇部興産株式会社宇部研究所内

(72)【発明者】

【氏名】中川　成人

【住所又は居所】山口県宇部市大字小串１９７８番地の５　宇部興産株式会社宇部研究所内

(72)【発明者】

【氏名】大坪　英樹

【住所又は居所】山口県宇部市大字小串１９７８番地の５　宇部興産株式会社宇部研究所内

(74)【代理人】

【識別番号】１００００７７５１７

【弁理士】

【氏名又は名称】石田　敬　（外３名）

【テーマコード（参考）】4L037

【Ｆターム（参考）】4L037 CS17 CS22 FA03 FA05 PA31

(57)【要約】

【課題】　室温から高温まで引張強度が大きい無機繊維を提供すること。

【解決手段】　Ｌｎ（Ｌｎは少なくとも一種の希土類金属元素）、Ａ（ＡはＡｌ，Ｃｒ，Ｆｅ及びＧａからる群から選択される少なくとも一種の元素）及びＯから構成される溶融液を回転ロールに接触させて冷却し、細線状に凝固させて製造されるＬｎ、Ａ、及びＯから構成される繊維を７００～１７００℃で加熱することにより製造される、結晶質の$Ln_3A_5O_{12}$相、結晶質の$LnAO_3$相及び結晶質のA_2O_3相からなる群から選択される少なくとも二種の結晶質相から構成される高耐熱性無機繊維。

[Address] Miyagi Prefecture Sendai City Aoba-ku Kawauchi Mohasekura 3 5　Kawauchi Residence 11 - 806

(72) [Inventor]

[Name] Kazuhisa　Yoshiharu

[Address] Inside of Yamaguchi Prefecture Ube City Oaza Okusl 197 8-5　Ube Industries Ltd. (DB 69-056-0008) Ube Research Laboratory

(72) [Inventor]

[Name] Nakagawa　adult

[Address] Inside of Yamaguchi Prefecture Ube City Oaza Okusl 197 8-5　Ube Industries Ltd. (DB 69-056-0008) Ube Research Laboratory

(72) [Inventor]

[Name] Otsubo　Hideki

[Address] Inside of Yamaguchi Prefecture Ube City Oaza Okusl 197 8-5　Ube Industries Ltd. (DB 69-056-0008) Ube Research Laboratory

(74) [Attorney(s) Representing All Applicants]

[Applicant Code] 100077517

[Patent Attorney]

[Name] ISHIDA　TAKASHI　(3 OTHERS)

[Theme Code (Reference)] 4L037

(57) [Abstract]

[Problem]　Offer inorganic fiber where tensile strength is large rom room temperature to high temperature.

[Means of Solution]　Ln (As for Ln rare earth metal element of at least one kind), Contacting roll, it cools molten liquid which is formed from theA (As for A from Al , Cr , Fe るはGa selected from thegroup element of at least one kind which) and O, solidification doing in fine line, high heat resistance inorganic fiber which is formed from crystalline phaseof at least two kinds which is selected from group which is produced byheating fiber which is formed from Ln, A, and O which are produced with 700 to 1700 °C, consists of crystalline Ln3 A5 O12phase, crystalline L nA O3 phase and crystalline A2 O3 phase.

【特許請求の範囲】|

【請求項１】　Ｌｎ（Ｌｎは少なくとも一種の希土類金属元素）、Ａ（ＡはＡｌ，Ｃｒ，Ｆｅ及びＧａからなる群から選択される少なくとも一種の元素）及びＯから構成される溶融液を回転ロールに接触させて冷却し、細線状に凝固させて製造されるＬｎ、Ａ、及びＯから構成される繊維を７００～１７００℃で加熱することにより製造される、結晶質の$Ln_3 A_5 O_{12}$相、結晶質の$LnAlO_3$相及び結晶質の$A_2 O_3$相からなる群から選択される少なくとも二種の結晶質相から構成される高耐熱性無機繊維。

【請求項２】　ＡがＡｌ及び／又はＣｒである請求項１記載の高耐熱性無機繊維。

【請求項３】　各々の結晶質相が繊維中に均一に分散して存在し、かつその粒子径が揃っていることを特徴とする請求項１又は２記載の高耐熱性無機繊維。

【請求項４】　希土類金属元素が、Ｅｒ，Ｙｂ，Ｄｙ，Ｙ，Ｇｄ，Ｌａ，Ｓｍ，Ｃｅ，Ｐｒ，Ｎｄ，Ｅｕ，Ｔｂ，Ｈｏ，Ｔｍ及びＬｕからなる群から選択される少なくとも一種の元素であることを特徴とする請求項１～３に記載の高耐熱性無機繊維。

【請求項５】　希土類金属元素が、Ｅｒ，Ｙｂ及びＤｙからなる群から選択される少なくとも一種の元素であることを特徴とする請求項４に記載の高耐熱性無機繊維。

【発明の詳細な説明】

【０００１】

【発明の属する技術分野】本発明は、断熱材、フィルタ材またはプラスチック、金属、セラミックス、コンクリート等の強化材等その他広範な用途に使用される無機繊維に関するものである。

【０００２】

【従来の技術】金属の弾性率及び高温強度の改善、セラミックスの靭性の改善等を目的として、$Al_2 O_3$系、ＳｉＣ系等の連続繊維をその強化材として適用するための研究開発が活発に行われている。$Al_2 O_3$系繊維は、高温における耐酸化性が良好なことや溶融金属に対して比較的安定であることなどから、上記用途への適用が期待されている。しかしながら、$Al_2 O_3$系繊維は、

[Claim(s)]

[Claim 1] Ln (As for Ln rare earth metal element of at least one kind), Contacting roll, it cools molten liquid which is formed from theA (As for A is selected from group which consists of theAl , Cr , Fe and Ga element of at least one kind which) and O, solidification doing in fine line, high heat resistance inorganic fiber which is formed from crystalline phaseof at least two kinds which is selected from group which is produced byheating fiber which is formed from Ln, A, and O which are produced with 700 to 1700 °C, consists of crystalline Ln3 A5 O12phase, crystalline L nA O3 phase and crystalline A2 O3 phase.

[Claim 2] High heat resistance inorganic fiber which is stated n Claim 1 where A is Al and/or Cr.

[Claim 3] Each crystalline phase dispersing to uniform in fiber it exists, high heat resistance inorganic fiber which is stated in Claim 1 or 2 which designates that at same timethe particle diameter has been even as feature.

[Claim 4] Rare earth metal element, high heat resistance inorganic fiber which is stated in Claim 1 to 3 which designatesthat it is a element of at least one kind which is selected from group whichconsists of Er,Yb,Dy,Y,Gd,La,Sm,Ce,Pr,Nd,Eu,Tb,Ho, Tm and Lu as feature.

[Claim 5] Rare earth metal element, high heat resistance inorganic fiber which is stated in Claim 4 which designatesthat it is element of at least one kind which is selected from group whichconsists of Er,Yb and Dy as feature.

[Description of the Invention]

[0001]

[Technological Field of Invention] This invention, is in addition something such as insulation regarding inorganic fiberwhich is used for broad application, filter or plastic , metal , ceramic and concrete or other reinforcement.

[0002]

[Prior Art] With modulus of metal and improvement of high temperature strength and theimprovement etc of toughness of ceramic as object, Al2O3 system,the research and development in order to apply SiC or other continuous fiber as reinforcement is doneactively. As for Al2O3 fiber, fact that etc it is a stability relativelyfrom fact that oxidation resistance in high temperature is satisfactory andvis-a-vis molten metal,

例えば１２００℃以上の温度においてその強度が低下するなど、セラミックス強化用としては耐熱性が十分に高くない。したがって、高温における耐酸化性が良好な酸化物であって、Al_2O_3系繊維以上の高耐熱性を有する繊維の開発が待たれている。|

application to above-mentioned application isexpected. But, strength heat resistance is not high in fully it decreases suchas, as ceramic reinforcement as for Al2O3 fiber, in temperature of for example 1200 °C or higher. Therefore, being a oxide where oxidation resistance in high temperature is satisfactory, development of fiber which possesses high heat resistance abov Al2O3fiber is expected.

【０００３】米国特許第５，６０５，８７０号には、１０poises以下の粘度を有する溶融液より製造されるセラミックファイバーが開示されている。この繊維は、それ自体公知のいわゆる melt extraction法により製造され、非晶質相及び／又は結晶相から構成されている。しかし、クレーム１の記載によると、「結晶粒径がlinearmatt surfaced line より放射線状に増加する」との限定があり、本発明による各々の結晶質相が繊維中に均一に分散して存在し、かつその粒子径が揃っている無機繊維とは異なるものである。

[0003] In U. S. Patent No. 5,605,870 number, ceramic fiber whi ch is produced is disclosed from themolten liquid which possess viscosity of 10 poise s or less. This fiber is produced by so-called melt extraction method of that itself public knowledge, isconstituted from amorphous phase and/or crystal phase. But, according to statement of claim 1, " crystal grain diameter from linear matt surface dl ine increases in radiating wires" wit there islimitation, each crystalline phase which is by this invention dispersing to uniformin fiber, it exists, inorganic fiber where at same time particle diameterhas been even is something which differs.

【０００４】

[0004]

【発明が解決しようとする課題】上記のような現状を鑑みて、本発明者らは、室温においても高温においても高強度を有し、高温における耐酸化性が良好な酸化物繊維を得るべく鋭意研究を重ね、本発明に記す新規な無機繊維を見出した。すなわち、Ｌｎ（Ｌｎは少なくとも一種の希土類金属元素）、Ａ（ＡはＡｌ，Ｃｒ，Ｆｅ及びＧａからなる群から選択される少なくとも一種の元素）及びＯから構成される溶融液を回転ロールに接触させて冷却し、細線状に凝固させて製造されるＬｎ、Ａ、及びＯから構成される繊維を７００～１７００℃で加熱することにより製造される、結晶質の$Ln_3A_5O_{12}$相、結晶質の$LnAO_3$相及び結晶質のA_2O_3相からなる群から選択される少なくとも二種の結晶質相から構成される無機繊維が、室温においても高温においても高強度を有することが見出された。

[Problems to be Solved by the Invention] As description above considering present state, in order that these inventorshas high strength regarding room temperature, and regarding high temperature obtains theoxide fiber where oxidation resistance ir high temperature is satisfactory, diligent research wasrepeated, novel inorganic fiber which is inscribed to this invention was discovered. namely, Ln (As for Ln rare earth metal element o at least one kind), Contacting roll, it cools molten liquid which is formed from theA (As for A is selected from group which consists of theAl , Cr , Fe and Ga element of at least one kind which) and O, solidification doing in fine line, it is produced Ln, inorganic fiber which is formed from crystalline phase of at least two kinds which isselected from group which is produced heating fiber beingformed from A, and O with 700 to 1700 °C, consists of crystalline Ln3 A5 O12 phase, crystalline L nA O3

high strength regarding room temperature and regarding high temperature.

【０００５】本発明の目的は、室温から高温までの引張強度が大きく、断熱材、フィルタ材またはプラスチック、金属、セラミックス、コンクリート等の強化材等その他広範な用途に好適に使用することができる無機繊維を提供することにある。

[0005] As for objective of this invention, tensile strength to hig h temperature is large fromthe room temperature, it is in addition such as insulation to offer inorganic fiber whichcan b used for ideal in broad application, filter or plastic , metal , ceramic and concrete or other reinforcement.

【０００６】

[0006]

【課題を解決するための手段】以下、本発明について詳細に説明する。本発明は、結晶質の$Ln_3A_5O_{12}$相（Ｌｎは少なくとも一種の希土類金属元素、ＡはＡｌ，Ｃｒ，Ｆｅ及びＧａからなる群から選択される少なくとも

[Means to Solve the Problems] You explain in detail below, cor cerning this invention. this invention crystalline Ln3 A5 O12 phase (As for Ln rare earth metal element of at least one kind, as for A is selectedfrom group which consists of Al , Cr ,

一種の元素）、結晶質のＬｎＡＯ$_3$相及び結晶質のＡ$_2$Ｏ$_3$相からなる群から選択される少なくとも二種の結晶質相から構成され、室温から１２００℃の温度範囲で高い強度を有する無機繊維に関する。

Fe and Ga element ofthe at least one kind which), is formed from crystalline phase of at least two kinds whichis selected from group which consists of crystalline L nA O3 phase and crystalline A2 O3 phase regards inorganic fiber which from room temperature possesses high strengthwith temperature range of 1200 °C.

【０００７】この無機繊維は、Ｌｎ（Ｌｎは少なくとも一種の希土類金属元素）、Ａ（ＡはＡｌ，Ｃｒ，Ｆｅ及びＧａからなる群から選択される少なくとも一種の元素）及びＯから構成される溶融液を回転ロールに接触させて冷却し、細線状に凝固させて製造されるＬｎ、Ａ、及びＯから構成される繊維を７００～１７００℃で加熱することにより製造されるものである。ここで、「結晶質」とは、透過電子顕微鏡観察によって結晶格子像を確認することができる相の原子構造を意味する。

[0007] It is something which is produced by heating fiber which is formedfrom Ln, A, and O where this inorganic fiber,the Ln (As for Ln rare earth metal element of at least one kind), contacting roll, cools molten liquid which is formedfrom A (As for A is selected from group which consists of theAl , Cr , Fe and Ga element of at least one kind which) and O, solidification does in fine line andis produced with 700 to 170(°C. Here, " crystalline " with, atom construction of phase which can verify crystal lattice imageby transmission electron microscope observation is meant.

【０００８】

[0008]

【発明の実施の形態】本発明におけるＬｎとしては、Ｅｒ，Ｙｂ，Ｄｙ，Ｙ，Ｇｄ，Ｌａ，Ｓｍ，Ｃｅ，Ｐｒ，Ｎｄ，Ｅｕ，Ｔｂ，Ｈｏ，Ｔｍ及びＬｕからなる群から選択される少なくとも一種の希土類金属元素が挙げられ、特に、Ｅｒ，Ｙｂ，Ｄｙは得られる無機繊維の強度が高くなるので好ましい。

[Embodiment of Invention] Be able to list rare earth metal elem ent of at least one kind which is selected from thegroup which consists of Er,Yb,Dy,Y,Gd,La,Sm,Ce,Pr,Nd,Eu,Tb,Ho, Tm anc Lu as Ln in thethis invention, because especially, as for Er,Yb, Dy strength of inorganic fiberwhich is acquired becomes high, i is desirable.

【０００９】Ａとしては、Ａｌ，Ｃｒ，Ｆｅ及びＧａからなる群から選択される少なくとも一種の元素が挙げられ、特に、ＡがＡｌ及び／又はＣｒの場合は得られる無機繊維の高温強度が高くなるので好ましい。

[0009] As A, be able to list element of at least one kind which i selectedfrom group which consists of Al , Cr , Fe and Ga, whenespecially, A is Al and/or Cr, because high temperature strength of inorganic fiberwhich is acquired becomes high it is desirable.

【００１０】本発明の無機繊維におけるＡの割合は、Ａ$_2$Ｏ$_3$換算で１０～９０モル%の範囲にあることが好ましい。本発明の無機繊維は、Ｌｎ$_3$Ａ$_5$Ｏ$_{12}$，ＬｎＡＯ$_3$，Ａ$_2$Ｏ$_3$で表わされる結晶相の群から選ばれる少なくとも二種の結晶相（例えばＡ$_2$Ｏ$_3$でもＡが異なれば異なる結晶相）で構成される実質的に結晶質相のみよりなるものであるが、結晶粒界には非晶質相が存在し得る。また、本発明の無機繊維の形状は、特に限定されないが、円形又は円形に近い断面を有することが好ましい。本発明の無機繊維は連続繊維としても短繊維としても使用できる。無機繊維の横断面の寸法は、断面形状にもより一概ではないが、３～５０μｍの直径を有するものが良く、５～３０μｍの直径を有するものがより好ましい。

[0010] As for ratio of A in inorganic fiber of this invention, it i s desirablewith A2 O3 conversion to be range of 10 to 90 mole%. inorganic fiber of this invention is constituted is something which consists ofonly crystalline phase substantially with crystal phase (If A differs even in for example A2 O3 , it differs crystal phase) of at least two kinds which ischosen from group of crystal phase which is displayed with Ln3 A5 O12,L nA O3 , A2 O3 ,but amorphous phase can exist in crystal grain boundary . In addition, shape of inorganic fiber of this invention is not limitedespecially. It is desirable to possess cros section which is close to round orthe round. As continuous fiber also as short fiber you can use inorganic fiber of this invention. dimension of cross-section of inorganic fiber is not more one approximation evenin cross section shape. Those which possess diameter of 3 to 50 m are good, those whichpossess diameter of 5 to 30 m are more desirable.

【００１１】本発明の無機繊維の室温、好ましくはさらに１２００℃における引張強度は、１．５GPa 以上、好

[0011] Room temperature of inorganic fiber of this invention, preferably furthermore as for thetensile strength in 1200 °C,

ましくは2．0GPa 以上であることが望ましい。本発明の無機繊維は、高い強度を有し、室温より１２００℃までの温度範囲ではその強度はほとんど温度依存性を示さないことから、例えば、セラミックスの強化用繊維や高温炉の断熱材等として特に有用である。

it is desirable to be a 1.5 GPa or greater and a preferably 2.0 GPa or greater. inorganic fiber of this invention has high strength, with temperature range to 1200 °Cas for strength especially it is useful from room temperature from factthat for most part temperature dependence is not shown, as reinforcement fiber of the for example ceramic and insulation etc of high temperature furnace.

【００１２】本発明の無機繊維は、Ｌｎ、Ａ及びＯから構成される溶融液を回転ロールに接触させて冷却し、細線状に凝固させて製造されるＬｎ、Ａ、及びＯから構成される繊維を７００～１７００℃で加熱することにより製造される。７００～１７００℃での加熱前の繊維（以下、中間繊維と記す）は、特願平９－３５３２７０号に記載された方法によって製造される。以下、その方法について詳細に説明する。

[0012] Inorganic fiber of this invention, contacting roll, cools molten liquid which isformed from Ln, A and O, clotting does in the fine line and is produced by heating fiber which is formec from theLn, A, and O which are produced with the700 to 1700 °C. fiber (Below , intermediate filament you inscribe.) before heating with 700 to 1700 °C is produced by methodwhich is stated in Japan Patent Application Hei 9 - 353270 number. You explain in detail below , concerning method.

【００１３】溶融前の原料としては、一般的にはＬｎの酸化物及びＡの酸化物が用いられるが、溶融したときに酸化物になるものであれば良く、水酸化物、炭酸塩等を用いても良い。原料の形態としては、粉体、成形体、焼結体、凝固体のいずれでも良く、また、これらの二つ以上が組み合わさったものでも良い。

[0013] As starting material before melting, generally it can use oxide of theLn and oxide of A, but when melting, if it issomething which becomes oxide, to be good, making use of hydroxide and carbonate etc it is good. As form of starting material, it is good with whichever of powder , the molded article , sinter and coagulant, in addition, these two or more unite and aregood being something which is brought together.

【００１４】前記の原料の溶融方法は、少なくとも該原料の回転ロールに接触する部分をその融点以上の温度に加熱することが可能な方法であればいかなる方法でも良く、加熱源として、例えば、アーク、レーザー、電子ビーム、光、赤外線、高周波等を用いることができる。高周波を用いる場合は、該原料が室温近傍においてほとんど導電性を有さないために、導電性を有しかつ該原料の融点より高い融点を有する坩堝に該原料を収容する必要がある。例えば、Ｍｏ，Ｗ，Ｔａ，Ｉｒ，Ｎｂ等の坩堝が好適に用いられる。また、原料が粉体である場合も上記のような材質の坩堝や支持台を用いる必要があるが、この場合は上記坩堝に加えて、水などによって冷却を施したＣｕ製の坩堝や支持台等を使用することもできる。原料が粉体である場合以外でもこれらの坩堝や支持台等を好適に使用することができる。

[0014] If dissolving method of aforementioned starting materia l is method whoseit is possible to heat portion which at least contacts roll ofthe said starting material to temperature of melting point or higher, it is good any method, it can usethe for example arc , laser , electron beam , light, infrared light and high frequency etc asthe heat source. When high frequency is used, said starting material because for most part i doesnot possess electrical conductivity in room temperature vicinity, electrical conductivity it is necessary toaccommodate said starting material in crucible which possesses high melting point from themelting point of possessing and said starting material. It can use for ideal for example Mo,W,Ta,Ir,Nb or other crucible. In addition, when starting material is powder, a description above thecrucible of material and it is necessary to use support table, but in thiscase it can also use crucible and support table etc of Cu makewhich administers cooling in addition to above-mentioned crucible,with water etc. When starting material is powder, these crucible and support table etc can be usedfor ideal at in addition to.

【００１５】原料の溶解は、大気中、不活性ガス中、還元性ガス中、炭化水素ガス中、真空中などいかなる雰囲気中で行われても良いが、原料の融点以下の温度において酸化されやすい坩堝等を用いる場合は、アルゴンガスやヘリウムガスなどの不活性ガス雰囲気中または真空中などで溶解を行うことが好ましい。また、アークにより

[0015] Melting starting material is good being done, in atmosp here, in inert gas, inthe reductive gas, in hydrocarbon gas and in vacuum middle class whatever atmosphere,but when crucibl etc which oxidation is easy to be done is used inthe temperature of melting point or lower of starting material, it is desirable to melt at in orvacuum middle class argon gas and helium gas or

原料を溶解する場合は、アークが発生するに十分なアルゴンガス等が雰囲気中に含まれている必要がある。

other inert gas atmosphere. In addition, when starting material is melted with arc , arc occurshas necessity for sufficient argor gas etc to be included in atmosphere.

【００１６】回転ロールの材質には特に制限はないが、熱伝導率が大きいものや高融点金属などがロールの寿命や得られる繊維の品質の安定性の点で好ましい。具体的には、Ｃｕ、Ｃｕ合金、Ｍｏ，Ｔａ，Ｗ，Ｉｒ等を好適に使用することができる。回転ロールと溶融液との接触は、例えば、溶融液に回転ロールの先端を回転接触させる、あるいは回転ロール上に溶融液を落下させるなどのいずれの態様でも良い。ただし、回転ロールの形状としては、その先端が溶融液と小さい面積で接触することが可能なものが、得られる繊維の断面形状を均一にするのに都合が良く、例えば図１に示すように、先端にＶ字型の突起を有する回転ロールを好適に使用することができる。

[0016] There is not especially restriction in material of roll. T hing and high melting point metal etc where thermal conductivity is large are desirable inthe lifetime of roll and poin of stability of quality of thefiber which is acquired. Concretely, Cu , Cu alloy and Mo,Ta,W,Ir etc can be used forideal. Contact with roll and molten liquid end of roll turnscontacts for example molten liquid, or it is good or other any embodiment which molten liquidfalls on roll. However, as end molten liquid those whose it is possible with thesmall surface area to contact, are convenient in order to designatethe cross section shape of fiber which is acquired as uniform as shape ofthe roll, shown in for example Figure 1, roll which possesses protrusion ofthe V-shape in end can be used for ideal.

【００１７】このような回転ロールを溶融液に接触させる際の回転ロールの周速度は１０ｍ／sec 以下であることが望ましい。周速度が１０ｍ／sec より速い場合は、断面積が一定の繊維を得ることが難しくなる場合があるためである。

[0017] This kind of roll case where it contacts molten liquid as : or theperimeter velocity of roll it is desirable to be below 10 m/sec . When perimeter velocity is faster than 10 m/sec , is because there are timeswhen it becomes difficult for cross-sectional area to obtain fixed fiber.

【００１８】本発明の中間繊維を製造する装置としては、例えば図２に示すような機構を有するものを使用することができる。Ｗ電極（１）と水冷を施されたＣｕ製坩堝（２）の間に発生させたアーク（３）により溶解されたＬｎ、Ａ及びＯから構成される溶融液（４）をＣｕ製坩堝を横方向に移動させることにより矢印の方向に回転するロール（５）に接触させ、細線状に凝固させることで上記元素より構成される中間繊維（６）を得るものである。

[0018] Those which possess kind of mechanism which is shown in for example Figure 2 asthe equipment which produces intermediate filament of this invention, can be used. It was melted by arc (3) which occurs between Cu make crucible (2)which is administered W electrode (1) and water cooling Ln, Contacting roll (5) which turns to direction of arrow molten liquid (4)being formed from A and O by moving Cu makecrucible to transverse direction, it is something which obtains intermediate filament (6) which fromthe above-mentioned element consists of thing which solidification isdone in fine line.

【００１９】中間繊維から本発明の無機繊維への転換は、中間繊維を７００～１７００℃で加熱することにより行われる。熱処理の温度、時間、昇降温速度等を適宜選択することにより目的とする無機繊維を得ることができる。中間繊維の加熱方法は、該繊維を７００～１７００℃に加熱することが可能な方法であればいかなる方法でも良く、加熱源として、例えば、通電により発熱するＳｉＣ，$MoSi_2$ などの発熱体、高周波、レーザー、電子ビーム、光、赤外線等を用いることができる。

[0019] Conversion to inorganic fiber of this invention is done f rom intermediate filament by heatingthe intermediate filament with 700 to 1700 °C. inorganic fiber which is made objective temperature of thermal processing, by selecting time and heating and cooling rate etc appropriately can be acquired. If heating method of intermediate filament is method whose it is possible to heatthe said fiber to 700 to 1700 °C, it is good any method, it can use SiC,MoSi2 or other heat emitter ,the high frequency , laser , electron beam , light and infrared light etc which theheat emission are done as heat source, with for example electrification.

【００２０】一般的には、Al_2O_3，ＳｉＣ等のセラミックス、Ｍｏ，Ｔａ，Ｗ，Ｉｒ，Ｎｂ等の高融点金属製の坩堝等に中間繊維を収容して、坩堝ごと加熱を行う、または、同様の素材からなるドラムに中間繊維を巻き取り、ドラムごと加熱を行うなどの方法が用いられる。

[0020] Generally, accommodating intermediate filament in Al2 O3 ,SiC or other ceramic and crucible etc ofthe Mo,Ta,W,Ir,Nb or other high melting point metallic, every crucible it heats, or, every windup and drum theor other method which heats can use intermediate filament for drum which consists ofthe similar

他にも、所定の温度に昇温された管状炉の炉内に繊維を連続して通す方法などを適用することもできる。また、より高い強度を有する繊維を得るためには、結晶が繊維方向に成長するように、中間繊維が繊維の片側から繊維方向に徐々に加熱を受けるような一方向加熱を行うこともできる。この場合の加熱処理は、上述のような管状炉の炉内に繊維を連続して通す方法によっても可能であるが、レーザー、電子ビーム、光、赤外線等を用いて、繊維又は被加熱部を繊維方向に移動させる方法を適用することもできる。

material. In specified temperature continuing fiber inside furnace of tube furnace whichthe temperature rise is done is possible also fact that it applies method etc which it passes to in addition to. In addition, in order to obtain fiber which possesses a higherstrength, in order for crystal to grow in fiber direction, it ispossible also to do one direction kind of heating where intermediate filament from theone side of fiber gradually receives heating to fiber direction. It is possible also to apply method which moves fiber orsuffering heated part to fiber direction as for heat treatment in this case,continuing fiber inside furnace of tube furnace, an above-mentionedway it is possible but, making use of laser , electron beam , light andthe infrared light etc with method which it passes.

【００２１】中間繊維の加熱処理は、大気中、不活性ガス中、還元性ガス中、炭化水素ガス中、真空中などいかなる雰囲気中で行われても良いが、用いられる坩堝、ドラム等の材質により制限を受ける場合がある。

[0021] Heat treatment of intermediate filament is good being done, in atmosphere, in inert gas,in reductive gas, in hydrocarbon gas and in vacuum middle class whateveratmosphere, but there are times when restriction is received with crucible and drum or other material which are used.

【００２２】

【実施例】以下、実施例及び比較例を示して本発明についてさらに具体的に説明する。

[0022]

[Working Example(s)] Below, showing Working Example and Comparative Example, furthermore you explain concretelyconcerning this invention.

実施例１

Working Example 1

原料には$\alpha-Al_2O_3$粉末とEr_2O_3粉末を用いた。$\alpha-Al_2O_3$粉末とEr_2O_3粉末をモル比で前者を８１．１、後者を１８．９の割合でエタノールを用いた湿式ボールミルによって混合し、得られたスラリーからロータリーエバポレータを用いてエタノールを除去した。得られた混合粉末をステンレス製のダイスを用いて一軸プレスにより直径１０mm、高さ１０mmの円柱状に成形し、次いでこの円柱状成形体をアークにより溶解しボタン状の凝固体を得た。このボタン状凝固体を図２に示す水冷を施したＣｕ製坩堝（２）に収容し、その後、図２の機構が収容される系内を－０．０４MPa のアルゴンガス雰囲気にし、W電極とＣｕ製坩堝の間にアークを発生させた。アークによってボタン状凝固体を溶解し、この溶解状態を維持したまま、Ｃｕ製坩堝を移動させて、２m／sec の周速度で回転する先端に３０° のＶ字型突起を有する直径７０mmのＣｕ製ロールに接触させ、平均直径１５μmの連続繊維を得た。次いで、この中間繊維をAl_2O_3製の坩堝に収容し、$MoSi_2$製の発熱体が装着された箱型の電気炉を用いて空気中で加熱処理を行った。１０００℃／hrの速度で昇温し、１４００℃で２hr保持した後に降温し、平均直径１４μmの連続繊維を得た。得られた繊維は、Ｃｕ－Kα線を用いたＸ線回折及び走査電子顕微鏡観察により、複数の１００～１５０nmの$Er_3Al_5O_{12}$相及び複数の１００～１５０nm

- Al2O3 powder and Er2 O3 powder were used to starting material . - Al2O3 powder and Er2 O3 powder former 81.1 and the latter were mixedwith mole ratio with wet ball mill which uses ethanol at ratio of the18.9, ethanol was removed making use of rotary evaporator fromthe slurry which is acquired. mixed powder which is acquired making use of die of thestainle steel it formed in cylinder of diameter 10 mm and height 10 mm with thesingle screw press , next it melted this cylinder molded article with arc and acquired coagulantof button. It accommodated in Cu make crucible (2) which administers wate coolingwhich shows this button coagulant in Figure 2 after tha itdesignated inside of system where mechanism of Figure 2 is accommodated asthe argon gas atmosphere of - 0.04 MPa , generated arc between W electrode and theCu make crucible. I melted button coagulant with arc, while this dissolved state is maintained,moving Cu make crucible, contacting Cu make roll of thediameter 70 mm which possesses V-shape protuberance of 30 ° in end which turnswith perimeter velocity of 2 m/sec , it acquired continuous fiber of average diameter 15 m. Next, this intermediate filament was accommodated in crucible of Al2O3 make, theheat treatment was done in air making use of electric furnace of box shape wherethe heat emitter of MoSi2 make is mounted. temperature rise it did with rate of 1000 °C/hr, 2 hr after keeping,the cooling it did with 1400 °C,

のＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を、室温の場合は負荷速度２㎜／min 、スパン２５㎜の条件で、１０００℃及び１２００℃の空気中の場合は負荷速度２㎜／min 、スパン１００㎜の条件で行った。測定された室温、１０００℃及び１２００℃での引張強度の平均値を表１に示す。

acquired continuous fiber of average diameter 14 m. fiber which is acquired, it was a crystalline which is formedfrom Er3 Al 5 O12 phase of 100 to 150 nm of plural and Al2O3 phase of the100 to 150 nm of plural by X-ray diffraction and scanning electron microscope observation which usethe CuK - line, each crystal phase dispersed to uniform in fiber and itunderstood that it exists. In addition, tensile test of this fiber, in case of room temperature when withthe condition of load rate 2 mm/min and span 25 mm, it is in air of 1000 °C and 1200 °C, it did with condition of load rate 2 mm/min and span 100 mm. mean value of tensile strength with room temperature , 1000 °C and 1200 °C whichwere measured is shown in Table 1.

【００２３】実施例２

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＹｂ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を８３．７、後者を１６．３とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１００～１５０㎚のＹｂ$_3$Ａｌ$_5$Ｏ$_{12}$相及び複数の１００～１５０㎚のＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

[0023] Working Example 2

In starting material proportion with mole ratio former other th an designatingthe 83.7 and the latter as 16.3, continuous fiber was acquired with themethod which is similar to Working Example 1 making use of - Al2O3 powder and theYb2 O3 powder. fiber which is acquired was crystalline which is formedfrom Yb3 Al 5 O12 phase of 100 to 150 nm of multiple and Al2O3 phase of the100 to 150 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２４】実施例３

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＤｙ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を７８．９、後者を２１．１とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１００～１５０㎚のＤｙ$_3$Ａｌ$_5$Ｏ$_{12}$相及び複数の１００～１５０㎚のＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

[0024] Working Example 3

In starting material proportion with mole ratio former other th an designatingthe 78.9 and the latter as 21.1, continuous fiber was acquired with themethod which is similar to Working Example 1 making use of - Al2O3 powder and theDy2 O3 powder. fiber which is acquired was crystalline which is formedfrom Dy3 Al 5 O12 phase of 100 to 150 nm of multiple and Al2O3 phase of the100 to 150 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２５】実施例４

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＹ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を８２、後者を１８とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１５０～２００㎚のＹ$_3$Ａｌ$_5$Ｏ$_{12}$相及び複数の１５０～２００㎚のＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が

[0025] Working Example 4

In starting material proportion with mole ratio former other th an designatingthe 82 and the latter as 18, continuous fiber was acquired with themethod which is similar to Working Example making use of - Al2O3 powder and theY2 O3 powder. fiber which is acquired was crystalline which is formedfrom Y3 Al 5 O12 phase of 150 to 200 nm of multiple and Al2O3

繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

phase of the150 to 200 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２６】実施例５

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＧｄ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を７８、後者を２２とし、中間繊維の加熱処理温度を１３００℃とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１２０～１６０nmのＧｄＡｌＯ$_3$相及び複数の１２０～１６０nmのＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

[0026] Working Example 5

In starting material proportion former 78 and the latter werede signated as 22 with mole ratio making use of - Al2O3 powder and theGd2 O3 powder, other than designating heat treatment temperature of intermediate filament as 1300 °C, thecontinuous fiber was acquired with method which is similar t Working Example 1. fiber which is acquired was crystalline which is formedfrom Gd Al O3 phase of 120 to 160 nm of multiple and Al2O3 phase of the120 to 160 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２７】実施例６

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＳｍ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を６９、後者を３１とした以外は実施例５と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１２０～１６０nmのＳｍＡｌＯ$_3$相及び複数の１２０～１６０nmのＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

[0027] Working Example 6

In starting material proportion with mole ratio former other th an designatingthe 69 and the latter as 31, continuous fiber was acquired with themethod which is similar to Working Example . making use of - Al2O3 powder and theSm2 O3 powder. fiber which is acquired was crystalline which is formedfrom Sm lO3 phase of 120 to 160 nm of multiple and Al2O3 phase of the120 to 160 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２８】実施例７

原料にα－Ａｌ$_2$Ｏ$_3$粉末とＬａ$_2$Ｏ$_3$粉末を用い、その混合比をモル比で前者を７７．５、後者を２２．５とし、また回転ロールの周速度を１ｍ／secにした以外は実施例５と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１２０～１６０nmのＬａＡｌＯ$_3$相及び複数の１２０～１６０nmのＡｌ$_2$Ｏ$_3$相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

[0028] Working Example 7

In starting material proportion former 77.5 and the latter were designated as 22.5 with mole ratio making use of - Al2O3 powder and theLa2 O3 powder, in addition other than designating perimeter velocity of roll asthe 1 m/sec , continuous fiber was acquired with method which is similar totl Working Example 5. fiber which is acquired was crystalline which is formedfrom La Al O3 phase of 120 to 160 nm of plural and Al2O3 phase of the120 to 160 nm of plural by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００２９】実施例８

[0029] Working Example 8

原料にCr_2O_3粉末とEr_2O_3粉末を用い、その混合比をモル比で前者を７８、後者を２２とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１５０～２００nmの$ErCrO_3$相及び複数の１５０～２００nmのCr_2O_3相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

In starting material proportion with mole ratio former other th an designatingthe 78 and the latter as 22, continuous fiber was acquired with themethod which is similar to Working Example making use of Cr2O3 powder and theEr2 O3 powder. fiber which is acquired was crystalline which is formedfrom Er Cr O3 phase of 150 to 200 nm of multiple and Cr2O3 phase of the150 to 200 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００３０】実施例９

[0030] Working Example 9

原料にCr_2O_3粉末とGd_2O_3粉末を用い、その混合比をモル比で前者を８０、後者を２０とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１５０～２００nmの$GdCrO_3$相及び複数の１５０～２００nmのCr_2O_3相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

In starting material proportion with mole ratio former other th an designatingthe 80 and the latter as 20, continuous fiber was acquired with themethod which is similar to Working Example making use of Cr2O3 powder and theGd2 O3 powder. fiber which is acquired was crystalline which is formedfrom Gd Cr O phase of 150 to 200 nm of multiple and Cr2O3 phase of the150 to 200 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００３１】実施例１０

[0031] Working Example 10

原料にGa_2O_3粉末とGd_2O_3粉末を用い、その混合比をモル比で前者を６９．２、後者を３０．８とした以外は実施例１と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１５０～２００nmの$Gd_3Ga_5O_{12}$相及び複数の１５０～２００nmのGa_2O_3相から構成された結晶質であり、各々の結晶相が繊維中に均一に分散して存在していることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

In starting material proportion with mole ratio former other th an designatingthe 69.2 and the latter as 30.8, continuous fiber was acquired with themethod which is similar to Working Example 1 making use of Ga 2 O3 powder and theGd2 O3 powder. fiber which is acquired was crystalline which is formedfrom Gd3 Ga 5 O12 phase of 150 to 200 nm of multiple and Ga 2 O3 phase of the150 to 200 nm of multiple by analysis which is similar to Working Example 1, eachcrystal phase dispersed to uniform in fiber and it understood that itexists. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００３２】比較例１

[0032] Comparative Example 1

原料に$\alpha-Al_2O_3$粉末とZrO_2粉末を用い、その混合比をモル比で前者を６２、後者を３８とし、また回転ロールの周速度を０．５m／secにした以外は実施例５と同様の方法で連続繊維を得た。得られた繊維は実施例１と同様の分析により、複数の１００～１５００nmのZrO_2相、複数の１００～１０００nmのAl_2O_3相から構成されており、相対的に粗大な結晶相がロールの接触部分から放射線状に成長していることがわかった。

In starting material proportion former 62 and the latter werede signated as 38 with mole ratio making use of - Al2O3 powder and theZrO2 powder, in addition other than designating perimeter velocity of roll asthe 0.5 m/sec , continuous fiber wa: acquired with method which is similar tothe Working Example fiber which is acquired was formed from ZrO2 phase ofthe 100 to 1500 nm of plural and Al2O3 phase of 100 to 1000 nm of plural bythe analysis which is similar to Working Example 1, i

つまり、この繊維の組織は不均一であることがわかった。また、この繊維の引張試験を実施例１と同様にして行った結果を表１に示す。

understoodthat relatively coarse, large crystal phase from contacting portion of roll grows in theradiating wires. In other words, as for weave of this fiber it understood that itis a nonuniform. In addition, result of doing tensile test of this fiber in sameway as Working Example 1 is shown in Table 1.

【００３３】

[0033]

【表１】

[Table 1]

	原料組成	ロール周速度 (m/s)	加熱処理温度 (℃)	平均直径 (μm)	引張強度 (GPa) 室温	1000℃	1200℃
実施例１	Al_2O_3/Br_2O_3	2	1400	14	2.20	2.23	2.17
実施例２	Al_2O_3/Yb_2O_3	2	1400	13	2.13	2.15	2.11
実施例３	Al_2O_3/Dy_2O_3	2	1400	15	2.11	2.20	2.15
実施例４	Al_2O_3/Y_2O_3	2	1400	14	1.61	1.65	1.61
実施例５	Al_2O_3/Gd_2O_3	2	1300	11	2.01	1.99	1.95
実施例６	Al_2O_3/Sm_2O_3	2	1300	12	1.89	1.89	1.83
実施例７	Al_2O_3/La_2O_3	1	1300	9	1.82	1.72	1.68
実施例８	Cr_2O_3/Er_2O_3	2	1300	13	1.97	1.77	1.58
実施例９	Cr_2O_3/Gd_2O_3	2	1300	13	1.75	1.69	1.53
実施例10	Ga_2O_3/Gd_2O_3	2	1300	15	1.89	1.67	1.51
比較例１	Al_2O_3/ZrO_2	0.5	1300	14	0.68	0.71	0.33

【００３４】

[0034]

【発明の効果】本発明によれば、高温における耐酸化性が良好な酸化物であり、室温から高温までの引張強度が大きく、断熱材、フィルタ材又はプラスチック、金属、セラミックス、コンクリート等の強化材等その他広範な用途に好適に使用することができる無機繊維が提供される。

[Effects of the Invention] According to this invention, it is a oxide where oxidation resistance in high temperature issatisfactory, tensile strength to high temperature is large from room temperature, inaddition inorganic fiber which such as insulation can be used for ideal in thebroad application, filter or plastic , metal , ceramic and concrete or other reinforcement is offered.

【図面の簡単な説明】

[Brief Explanation of the Drawing(s)]

【図１】図１は、本発明の無機繊維の中間繊維の製造に用いる回転ロールの形状の一例を示す図面である。

[Figure 1] Figure 1 is drawing which shows one example of geo etry of rollwhich is used for production of intermediate filament of inorganic fiber of the this invention.

【図２】図２は、本発明の無機繊維の中間繊維の製造に用いる装置の機構の一例を示す図面である。

[Figure 2] Figure 2 is drawing which shows one example of mec anism of equipmentwhich is used for production of intermediate filament of inorganic fiber of the this invention.

【符号の説明】

1…W電極

2…Ｃｕ製坩堝

3…アーク

4…溶融液

5…ロール

6…中間繊維

[Explanation of Reference Signs in Drawings]

1...W electrode

2... Cu make crucible

3... arc

4... molten liquid

5... roll

6... intermediate filament

【図１】

[Figure 1]

図１



【図２】

[Figure 2]

図２